

## CERTIFICATE OF ANALYSIS

22 NOV 2016

Ship To:

QINGDAO XUTAI CHEMICALS CO., LTD. RM.1905, GUANGDONG DEVELOPMENT BANK BUILDING, NO.40 SHANDONG ROAD

266071 QINGDAO

China

Sold To:

QINGDAO XUTAI CHEMICALS CO., LTD. RM.1905, GUANGDONG DEVELOPMENT BANK BUILDING, NO.40 SHANDONG ROAD

266071 QINGDAO

China

Material Description:

Eastman(TM) Cellulose Acetate Butyrate (CAB-551-0.2) 20 KG (44

0 LB), Bag

Customer Order :

ESM161021 /

Outbound Delivery : Shipper Sales Order :

37186845000050 2380220

Ship Date

: 22 NOV 2016

Batch / Lot

: BA-24236B

Vehicle No Total # of Packages

: NYKU0757987

Net Weight, KG

330.000 6,600.000

Characteristic	Value	Lower Limit	Upper Limit	
Acetyl, W%	1.27			
Butyryl, W%	51.79	0.00 49.00	4.00	
Free Acidity by IC, PPM	90	0	300	
Moisture, W%	1.00	0.00	3.00	
Hydroxyl, W%	2.03	1.40	2.40	
ASTM-A Viscosity, s	0.166	0.160	0.250	
Manufacturing Date	14.09.2016			

No set shelf life for cellulose esters has been established. Its useful life is dependent upon the storage conditions. See the Material Safety Data Sheet for storage and handling information. For documentation purposes, the expiration date my be considered as five years from the date of manufacture.

Doug Booton

Quality Assurance Representative

jdbooton@eastman.com Phone no. (423) 224-9299